



DuraPro™



DuPont™ DuraPro™ fabric technology provides workers in the oil & gas, utilities, petrochemical, mining, manufacturing and transportation industries with inherent arc flash and FR protection at an affordable price. Garments made with DuraPro™ feel lightweight and are breathable to keep the wearer comfortable.

DuraPro™ offers >8 cal/cm² ATPV arc flash protection and is certified to NFPA 2112.

Extreme protection



Arc flash protection along with heat and flame resistance



Better protection at longer exposures and higher temperatures



Inherent protection; can't be washed out or worn away



Resists tears and abrasion

Color

This is a representation of the true color.



Navy



Royal blue



Red



Orange



Dark green



Khaki

Weight

6.5 oz/yd² / 220 g/m²

Fiber blend

Aramid, cotton, modacrylic

Hazards



Arc flash



Flash fire

Certifications

*Meets test requirements but certification pending.

ASTM F1506*

NFPA 2112

CGSB 155.20

ISO 11612

IEC 61482-2*

Fabric protection performance

Property	Standard	Units/description	DuraPro™
Fabric construction	—	—	Twill weave
Basis weight	—	oz/yd ² (g/m ²)	6.5 (220)
Arc rating (Arc Thermal Performance Value [ATPV])	IEC 61482-1-1	cal/cm ²	>8 (8.1)
Thermal manikin	NFPA 2112	TPBI (%)	16.9

Typical physical properties (ASTM, NFPA)

Property	Standard	Units/description	DuraPro™
Fabric construction	—	—	Twill weave
Basis weight	ASTM D3776	oz/yd ²	6.5
Tensile strength (Grab test)	ASTM D5034	Warp (lbf) Weft (lbf)	178 136
Elmendorf tear	ASTM D1424	Warp (lbf) Weft (lbf)	9 8
Dimensional stability after 5 cycles	AATCC 135	Machine (%) Cross (%)	<3 <3

Typical physical properties (ISO, EN)

Property	Standard	Units/description	DuraPro™
Fabric construction	—	—	Twill weave
Basis weight	ISO 3801	g/m ²	220
Tensile strength	ISO 13934-1	Warp (N) Weft (N)	972 696
Tear strength	ISO 13937-2	Warp (N) Weft (N)	13.6 15
Dimensional stability after 5 cycles	ISO 5077	Machine (%) Cross (%)	<3 <3

Suitable to be used for arc flash protection as per NEC, NESC, NFPA 70E and OSHA requirements.



dpp.dupont.com

DuPont Personal Protection
 @DuPontPPE

Product safety information is available upon request. All data are from certification and DuPont internal tests. Data can vary among testing labs.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DUPONT MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

© 2021 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. (3/21)